

# HAW-W03

TM-HAW-W03-10/10

## Technical Data Sheet

### Description

HAW-W03 is a self vulcanizing soft rubber based on chloroprene rubber (CR) which can also be applied and vulcanized on site.

The layer thickness of the rubber sheet may range between 3 and 6 mm.

### Main Application

Predominantly applied to protect steel and concrete structures from chemical attack.

### Range of Application

HAW-W03 is used as a protective lining for structural components made of steel and concrete which are subjected to chemical exposure.

#### resistant:

- + acid at lower concentrations
- + lye, brines

### Physical Data

Material Properties	Unit	Value	Technical Standard
Hardness	Shore A	70 ± 5	DIN 53505
Specific weight	g/cm <sup>3</sup>	1,61 ± 0,02	DIN EN ISO 1183
Tensile strength <sup>*)</sup>	MPa	≥ 5	DIN 53504
Elongation at break <sup>*)</sup>	%	> 250	DIN 53504
Rubber-metal-adhesion peeling test	N/mm	≥ 3	DIN EN 14879-4
Max. service temperature	°C	80	-
Testing Voltage	kV/mm	5	-

\*) The Values were determined at 4 mm thick rubber samples.

The technical data contained herein represents the current state of our product knowledge and is intended to furnish general information regarding our products and their application spectrum. In view of the diversity and multitude of application possibilities, this data should be regarded solely as general information, which does not guarantee any specific properties and/or suitability of these products for each concretely case of application. Consequently, when ordering a product, please contact us for detailed information relative to the properties required for a specific application. Our technical service will, upon request, furnish a profile of characteristics for the concretely application without delay.

### HAW Linings GmbH

Werkstraße 30 – 33, D-31167 Bockenem

Phone: +49 (0) 5067 990 0 / Fax.: +49 (0) 5067 990 2772 / [www.haw-linings.com](http://www.haw-linings.com)

TM-HAW-W03 (e)Rev 10-10.docx